

## **APPENDIX**

*Encyclopedia of Chemical Technology*, Fourth Edition, Volume 19, Kirk-Othmer,  
John Wiley & Sons, 1996, pp. 881-883

KIRK-OTHMER

# ENCYCLOPEDIA OF CHEMICAL TECHNOLOGY

FOURTH EDITION

VOLUME 19

PIGMENTS  
TO  
POWDERS, HANDLING



A Wiley-Interscience Publication  
**JOHN WILEY & SONS**

New York • Chichester • Brisbane • Toronto • Singapore

This text is printed on acid-free paper.

Copyright © 1996 by John Wiley & Sons, Inc.

All rights reserved. Published simultaneously in Canada.

Reproduction or translation of any part of this work beyond that permitted by Sections 107 or 108 of the 1976 United States Copyright Act without the permission of the copyright owner is unlawful. Requests for permission or further information should be addressed to the Permissions Department, John Wiley & Sons, Inc., 605 Third Avenue, New York, NY 10158-0012.

#### Library of Congress Cataloging-in-Publication Data

Encyclopedia of chemical technology/executive editor, Jacqueline

I. Kroschwitz; editor, Mary Howe-Grant.—4th ed.

p. cm.

At head of title: Kirk-Othmer.

"A Wiley-Interscience publication."

Contents: v. 19, Pigments to Powders, Handling

ISBN 0-471-52688-6 (v. 19)

1. Chemistry, Technical—Encyclopedias. I. Kirk, Raymond E.

(Raymond Eller), 1890–1957. II. Othmer, Donald F. (Donald

Frederick), 1904–1995. III. Kroschwitz, Jacqueline I., 1942–

IV. Howe-Grant, Mary, 1943–. V. Title: Kirk-Othmer encyclopedia of chemical technology.

TP9.E685 1992

660'.03—dc20

91-16789

Printed in the United States of America

10 9 8 7 6 5 4 3 2 1

Pigments  
Pilot Plants  
Pipelines  
Piping System  
Plant Layout  
Plant Location  
Plant Safety  
Plasma Technology  
Plasticizers  
Plastics Processing  
Plastics Testing  
Platinum-Growth  
Platinum-Growth  
Compound  
Plutonium and  
Compound  
Polishes

- O. Olabisi, L. M. Robeson, and M. T. Shaw, *Polymer-Polymer Miscibility*, Academic Press, Inc., New York, 1979.
- K. Solc, ed., *Polymer Compatibility and Incompatibility: Principles and Practice*, MMI Press Symposium Series, Vol. 2, Harwood Academic Publishers GmbH, New York, 1982.
- D. J. Walsh, J. S. Higgins, and A. Maconnachie, eds., *Polymer Blends and Mixtures*, NATO ASI Series, Series E, Applied Sciences, No. 89, Martinus Nijhoff Publishers, Dordrecht, the Netherlands, 1985.
- L. A. Utracki, *Polymer Alloys and Blends*, Hanser, Munich, Germany, 1989.
- B. M. Culbertson, ed., *Multiphase Macromolecular Systems, Contemporary Topics in Polymer Science*, Vol. 6, Plenum Publishing Corp., New York, 1989.
- M. M. Coleman, J. F. Graf, and P. C. Painter, *Specific Interactions and the Miscibility of Polymer Blends*, Technomic, Lancaster, Pa., 1991.
- I. S. Miles and S. Rostami, eds., *Multicomponent Polymer Systems*, Longman, Essex, U.K., 1992.
- A. A. Collyer, ed., *Rubber-Toughened Engineering Plastics*, Chapman and Hall, London, 1994.

H. KESKKULA  
D. R. PAUL  
J. W. BARLOW  
University of Texas at Austin

## POLYMERS


Polymers are very large molecules made by covalently binding many smaller molecules. The word polymer is derived from the Greek *poly* (many) and *meros* (part). The size of polymer molecules imparts many interesting and useful properties not shared by low molecular weight materials. Polymers are the fundamental materials of plastics, rubbers and most fibers, and surface coatings and adhesives, and as such are essential to modern society. Also, many important constituents of living organisms, eg, proteins (qv) and cellulose (qv), are biopolymers (qv).

### Classification and Nomenclature

Polymers were initially classified according to their response to temperature. Those that are softened (plasticized) reversibly by heat are known as thermoplastics. By analogy, wax behaves as a thermoplastic. Others, though they might initially be liquid or soften once upon heating, undergo a curing (setting) reaction that solidifies them, and further heating leads only to degradation. These are known as thermosets. Again by analogy, an egg behaves as a thermoset. The ability of polymers to soften and flow at least once is one of their most

valuable assets, as it allows them to be formed into complex shapes easily and inexpensively.


In general, polymers are formed by two types of reactions: condensation and addition. The formation of a polyester by polycondensation may be illustrated as follows.



In the polyester formula shown, parentheses enclose the repeating unit. The quantity  $x$  is the degree of polymerization, sometimes also called the chain length, the number of repeating units strung together like identical beads on a string. Neglecting the ends of the molecule, which is usually justified for large  $x$ , the molecular weight  $M$  of the polymer molecule is given by  $M = mx$ , where  $m$  is the molecular weight of the repeating unit. Since  $x$  can easily be in the thousands, it is not surprising that the term macromolecules is also used to describe these materials.


The ester linkage in the repeating unit characterizes polyesters.  $R$  and  $R'$  represent portions of the monomer molecule that do not participate in the polymerization. They may vary widely, giving rise to many different polyesters. Poly(ethylene terephthalate) (PET), made from ethylene glycol ( $R = (\text{CH}_2)_2$ ) and terephthalic acid ( $R' = \text{—}\bigcirc\text{—}$ ), is familiar in the form of soda bottles, recording tape, and polyester fiber (see FIBERS, POLYESTER).

Another common polycondensation involves reaction of diamines and diacids to form polyamides, commonly called nylons:



The amide linkage characterizes nylons. In the first commercial nylon, nylon-6,6,  $R = (\text{CH}_2)_6$  and  $R' = (\text{CH}_2)_4$ . Nylon-6,6 is familiar as a textile fiber (nylon stockings) and a molded plastic (see POLYAMIDES).

The two complementary functional groups that react to form condensation polymers may also occur in a single monomer, eg, a hydroxy acid,  $\text{HO}-\text{R}-\text{COOH}$ ; or an amino acid,  $\text{H}_2\text{N}-\text{R}-\text{COOH}$ . In some cases, such monomers self-condense to a cyclic structure, which is what actually polymerizes. For example,  $\epsilon$ -caprolactam (1) can be thought of as the self-condensation product of an amino acid. Caprolactam undergoes a ring-opening polymerization to form another



important  
in the acti  
tion polym

Addi  
bond to fo  
tion of etl


Because n  
identical t  
addition p  
(two doub  
one double  
per repeat  
vulcanizat

In te  
mers, illus  
is, can rea  
the exampl  
ent repeat  
with a ran  
random or  
with the p  
units are a  
poly(A-b-


A fev  
chains, eit  
A branche  
the branch  
are a mor  
they grow

As th  
reach from  
linked or  
polymeriz  
monomers  
formed lin  
liquid epo  
cured to a  
groups wil  
atoms are  
polymer m  
bowling ba

important nylon, nylon-6 (see CAPROLACTAM). Even though no water is eliminated in the actual polymerization step, the polymer is usually considered a condensation polymer. Table 1 illustrates some other important condensation polymers.



Addition or chain-growth polymerization involves the opening of a double bond to form new bonds with adjacent monomers, as typified by the polymerization of ethylene to polyethylene:



Because no molecule is split out, the molecular weight of the repeating unit is identical to that of the monomer. Vinyl monomers,  $\text{H}_2\text{C}=\text{CHR}$  (Table 2) undergo addition polymerization to form many important and familiar polymers. Diene (two double bonds) monomers also undergo addition polymerization. Normally, one double bond remains, leaving an unsaturated polymer, with one double bond per repeating unit. These double bonds provide sites for subsequent reaction, eg, vulcanization.

In terms of molecular structure, there are three principal categories of polymers, illustrated schematically in Figure 1. If each monomer is difunctional, that is, can react with other monomers at two points, a linear polymer is formed. All the examples given above are linear polymers. Polymers that contain two different repeating units, say A and B, are known as copolymers (qv). A linear polymer with a random (AABBABAAABABB) arrangement of the repeating units is a random or statistical copolymer, or just copolymer. It is termed poly(A-co-B), with the primary constituent listed first. A molecule in which the two repeating units are arranged in long, contiguous blocks  $([\text{A}]_x[\text{B}]_y)$  is a block (b) copolymer, poly(A-b-B).

A few points of tri- or higher functionality introduced along the polymer chains, either intentionally or through side reactions, give a branched polymer. A branched structure with the backbone consisting of one repeating unit (A) and the branches of another (B), is a graft (g) copolymer, poly(A-g-B). Dendrimers are a more recent development. They are molecules that branch repeatedly as they grow outward from a central core (1-3).

As the length and frequency of branches increase, they may ultimately reach from chain to chain. If all the chains are connected together, a cross-linked or network polymer is formed. Cross-links may be built in during the polymerization reaction by incorporation of sufficient tri- or higher functional monomers, or may be created chemically or by radiation between previously formed linear or branched molecules (curing or vulcanization). For example, a liquid epoxy (Table 1) oligomer (low molecular weight polymer) with  $x \approx 6-8$  is cured to a cross-linked solid by reaction of the hydroxyl and terminal epoxide groups with a diamine or acid anhydride. In a fully cross-linked polymer, all the atoms are connected to one another by covalent bonds, so the entire macroscopic polymer mass is literally a single molecule. Thus, the cross-linked polyester in a bowling ball has a molecular weight on the order of  $10^{27}$  g/mol.